



Baikalox Regular

PRODUCT CODE

CR10

Main applications



Transparent ceramic
phone/watch tops



Translucent ceramics
- PCA



Watch/Phone parts
polishing

TYPICAL VALUES

BET Specific Surface Area (m ² /g)	7	
Crystal Structure	95% Alpha	
TEM Ultimate Particle Size (nm)	350	
Particle Size Distribution (μm)	d20	0.25
	d50	0.45
	d90	1.25
Bulk Density (g/cm ³)	0.5	
Tapped Density (g/cm ³)	0.7	

CHEMICAL ANALYSIS

ICAP values (ppm)

Ca	2	Si	23	Na	12
Fe	4	K	15		

Typical values are given by Baikowski as an indication only. Such values are not contractual.

CONTACT NOW: sales@baikowski.com

BAIKOWSKI S.A.S.
1046 route de Chaumontet
BP 501 - 74330 POISY
FRANCE



Baikowski
PSB INDUSTRIES

www.baikowski.com

BAIKOWSKI JAPAN CO, LTD JAPAN | CHIBA
BAIKOWSKI CHINA CHINA | SHANGHAI
BAIKOWSKI KOREA CO, LTD KOREA | SEOUL
BAIKOWSKI INTERNATIONAL CORP USA | CHARLOTTE (NC)
BAIKOWSKI MALAKOFF INC USA | MALAKOFF (TX)