

Baikalox Regular



PRODUCT CODE

CR6


Main applications



Colored ceramics -
watch parts



Translucent ceramics
- PCA



UV-reflective coatings
- tube lamp



Ceramic coatings -
sensors



Li-ion batteries
separators coatings

TYPICAL VALUES

BET Specific Surface Area (m ² /g)	6
Crystal Structure	Alpha
TEM Ultimate Particle Size (nm)	400
Particle Size Distribution (μm)	d20 0.3
	d50 0.5
	d90 1.4
Bulk Density (g/cm ³)	0.6
Tapped Density (g/cm ³)	0.8

CHEMICAL ANALYSIS

ICAP values (ppm)

Ca	2	Si	22	Na	13
Fe	5	K	23		

Typical values are given by Baikowski as an indication only. Such values are not contractual.

CONTACT NOW: sales@baikowski.com

BAIKOWSKI S.A.S.
1046 route de Chaumontet
BP 501 - 74330 POISY
FRANCE



Baikowski
PSB INDUSTRIES

www.baikowski.com

BAIKOWSKI JAPAN CO, LTD JAPAN | CHIBA
BAIKOWSKI CHINA CHINA | SHANGHAI
BAIKOWSKI KOREA CO, LTD KOREA | SEOUL
BAIKOWSKI INTERNATIONAL CORP USA | CHARLOTTE (NC)
BAIKOWSKI MALAKOFF INC USA | MALAKOFF (TX)