



# Baikalox Regular

PRODUCT CODE

## GEA6

### Main applications



Colored ceramics –  
watch parts



Orthopedic & dental  
ceramics



Ceramic coatings –  
sensors

## TYPICAL VALUES

BET Specific Surface Area (m <sup>2</sup> /g)	5
Crystal Structure	Alpha
TEM Ultimate Particle Size (nm)	200
Particle Size Distribution (μm)	
d20	5
d50	8
d90	18
Bulk Density (g/cm <sup>3</sup> )	0.27
Tapped Density (g/cm <sup>3</sup> )	0.44

## CHEMICAL ANALYSIS

ICAP values (ppm)

Ca	2	Si	18	Na	13
Fe	4	K	12		

Typical values are given by Baikowski as an indication only. Such values are not contractual.

CONTACT NOW: [sales@baikowski.com](mailto:sales@baikowski.com)

**BAIKOWSKI S.A.S.**  
1046 route de Chaumontet  
BP 501 - 74330 POISY  
FRANCE



**Baikowski**   
PSB INDUSTRIES

[www.baikowski.com](http://www.baikowski.com)

**BAIKOWSKI JAPAN CO, LTD** JAPAN | CHIBA  
**BAIKOWSKI CHINA** CHINA | SHANGHAI  
**BAIKOWSKI KOREA CO, LTD** KOREA | SEOUL  
**BAIKOWSKI INTERNATIONAL CORP** USA | CHARLOTTE (NC)  
**BAIKOWSKI MALAKOFF INC** USA | MALAKOFF (TX)