




PRODUCT CODE

LSDBM

Main applications



Thermal adhesives - electronics



Electronic ceramics



Medical plastics polishing

TYPICAL VALUES

BET Specific Surface Area (m ² /g)	3.5
Crystal Structure	Alpha
Particle Size Distribution (µm) d50	1.1
Loss on ignition (%)	0.5
Green Density @ 5000 psi (g/cm ³)	2.28
Fired Density @ 1620°C / 1.5h (g/cm ³)	3.80
Linear shrinkage (%)	15.5

CHEMICAL ANALYSIS

ICAP values (ppm)

Ca	380	Si	370
Fe	100	Na	200

Typical values are given by Baikowski as an indication only. Such values are not contractual.

CONTACT NOW: sales@baikowski.com

BAIKOWSKI S.A.S.
1046 route de Chaumontet
BP 501 - 74330 POISY
FRANCE



Baikowski 
PSB INDUSTRIES

www.baikowski.com

BAIKOWSKI JAPAN CO, LTD JAPAN | CHIBA
BAIKOWSKI CHINA CHINA | SHANGHAI
BAIKOWSKI KOREA CO, LTD KOREA | SEOUL
BAIKOWSKI INTERNATIONAL CORP USA | CHARLOTTE (NC)
BAIKOWSKI MALAKOFF INC USA | MALAKOFF (TX)