




PRODUCT CODE

SA5CR

Main applications



UV-reflective coatings
– tube lamps



Li-ion batteries
separators coatings

TYPICAL VALUES

BET Specific Surface Area (m ² /g)	5
Crystal Structure	Alpha
Particle Size Distribution (µm)	
d10	0.2
d50	1.4
d90	5.3
Tapped Density (g/cm ³)	0.78
Green Density @ 5000 psi (g/cm ³)	1.74
Fired Density @ 1510°C / 2h (g/cm ³)	3.44

CHEMICAL ANALYSIS

ICAP values (ppm)

Ca	2	Si	14	Mg	2
Fe	4	Na	7		

Typical values are given by Baikowski as an indication only. Such values are not contractual.

CONTACT NOW: sales@baikowski.com

BAIKOWSKI S.A.S.
1046 route de Chaumontet
BP 501 - 74330 POISY
FRANCE



Baikowski 
PSB INDUSTRIES

www.baikowski.com

BAIKOWSKI JAPAN CO, LTD JAPAN | CHIBA
BAIKOWSKI CHINA CHINA | SHANGHAI
BAIKOWSKI KOREA CO, LTD KOREA | SEOUL
BAIKOWSKI INTERNATIONAL CORP USA | CHARLOTTE (NC)
BAIKOWSKI MALAKOFF INC USA | MALAKOFF (TX)